

**TECHNICAL DATA SHEET****Times collection/ FDW/
engineered**

Engineered oak boards, European manufacture , standard micro bevel (1x45°GO2), t&g on 4 sides, solid oak wear layer of between 3 and 5 mm, marine quality birch plywood support

DIMENSIONS:

- thickness: 16-18 mm
- width : 160-185-220 mm
- lengths: 90 % 2000-2450 mm

CHOICE:

- Rustic AB : filled or half-filled knots up to 60 mm, big knots tapped (1 tap for 2 m2) small knots remain open, discoloration and sap wood allowed

COLLECTION: times

STRUCTURE: aged - brushed - heavy brushed

GENERAL TECHNICAL DATA

Protective coat: 3 coats of Hard wax oil or 2 coats of varnish

Weight : 11 kg/m²

Thermal resistance: 0.11m².kw

Usage classification: C31 -

Fire class : M4 oiled : Dfl-s1-

UPEC classification : U3sP3E1C0

Shrinkage coefficients : radial oak 0.16,
tangential oak 0.32

Humidity ex works: 8-10 %

Wear classification: 33

EEC classification: respect norm E1
and EN 13489 (NF54011)

Compatible with new generation floor heating

**STORAGE:**

Store indoor.to maintain a stable flooring, relative air humidity is required to stay between 40-65 %

ADVISED FITTING :

Full glue (PU mono) about 1.4kg/m² or following glue-supplier advice

MAINTENANCE:

After fitting remove dirt and buff with white pad. In wet areas (kitchen, bathroom) extra coat of hard wax oil or varnish advised. Soap once a month with [CLR floor soap](#).(see instructions).Use maintenance [CLR HWO](#) 1-2 times a year depending on traffic (nourishes and saturates the parquet)

